

## Dental Materials Fact Sheet

Adopted by the Board on December 17, 2001

As required by Chapter 801, Statutes of 1992, the Dental Board of California has prepared this fact sheet to summarize information on the most frequently used restorative dental materials. Information on this fact sheet is intended to encourage discussion between the patient and dentist regarding the selection of dental materials best suited for the patient's dental needs. It is not intended to be a complete guide to dental materials science.

The most frequently used materials in restorative dentistry are amalgam, composite resin, glass ionomer cement, Resin ionomer cement, porcelain (ceramic), porcelain (fused-to-metal), gold alloys (noble) and nickel or cobalt chrome (based-metal) alloys. Each material has its own advantages and disadvantages, benefits and risks. These and other relevant factors are compared in the attached matrix filed "Comparisons of Restorative Dental Materials" A Glossary of Terms is also attached to assist the reader in understanding the terms used.

The statements made are supported by relevant credible dental research published mainly between 1993-2001. In some cases where contemporary research is sparse, we have indicated our best perceptions based upon information that predates 1993.

The reader should be aware that the outcome of dental treatment or durability of a restoration is not solely a function of the material from which the restoration was made. The durability of any restoration is influenced by the dentist's technique when placing the restoration, the ancillary materials used in the procedure, and the patient's cooperation during the procedure. Following restoration of the teeth, the longevity of the restoration will be strongly influenced by the patient's compliance with dental hygiene and home care, their diet and chewing habits.

Both the public and the dental profession are concerned about the safety of dental treatment and potential health risks that might be associated with the materials used to restore the teeth. All materials commonly used (and listed in this fact sheet) have been shown — through laboratory and clinical research, as well as through extensive clinical use — to be safe and effective for the general population. The presence of these materials in the teeth does not cause adverse health problems for the majority of the population. There exists a diversity of various scientific opinions regarding this safety of mercury dental amalgams. The research literature in peer reviewed scientific journals suggests that otherwise healthy women, children and diabetics are not at increased risk for exposure to mercury from dental amalgams. Although there are various opinions with regard to mercury risk in pregnancy, diabetes, and children, these opinions are not scientifically conclusive and therefore the dentist may want to discuss these opinions with their patients. There is no research evidence that suggest pregnant women, diabetics and children are at increased health risk from dental amalgam fillings in their mouth. A recent study reported in the JADA factors in a reduced tolerance (150% of the WHO safe limit) for exposure in calculating the amount of mercury that might be taken in from dental fillings. This level falls below the established safe limits for exposure to a low concentration of mercury or any other released component from a dental restorative material. Therefore, while these sub-populations may be perceived to be at increased health risk from exposure to dental restorative materials, the scientific evidence does not support that claim. However, there are individuals who may be susceptible to sensitivity, allergic or adverse reactions to selected materials. As with all dental materials, the risks and benefits should be discussed with the patient, especially with those in susceptible populations.

There are differences between dental materials and the individual elements or components that compose these materials. For example, dental amalgam filling material is composed mainly of mercury and varying percentages of silver, tin and copper. It should be noted that elemental mercury is listed on the Proposition 65 list of known toxins and carcinogens. Like all materials in our environment, each of these elements by themselves is toxic at some level of concentration if they are taken into the body. When they are mixed together, they react chemically to form a crystalline metal alloy. Small amounts of free mercury may be released from amalgam fillings over time and can be detected in bodily fluids and expired air. The important question is whether any free mercury is present in sufficient levels to pose a health risk. Toxicity of any substance is related to dose, and doses of mercury or any other elements that may be released from dental amalgam fillings falls far below the established safe levels as stated in the 1999 US Health and Human Services Toxicological Profile for Mercury Update.

All dental restorative materials (as well as all materials that we come in contact with in our daily life) have the potential to elicit allergic reactions in hypersensitive individuals. These must be assessed on a case-by-case basis, and susceptible individuals should avoid contact with allergenic materials. Documented reports of allergic reactions to dental amalgam exist (usually manifested by transient skin rashes in individuals who have come into contact with the material), but they are atypical. Documented reports of toxicity to dental amalgam exist, but they are rare. There have been anecdotal reports of toxicity to dental amalgam and as with all dental material risks and benefits of dental amalgam should be discussed with the patient especially with those in susceptible populations. Composite resins are the preferred alternative to amalgam in many cases. They have a long history of biocompatibility and safety. Composite resins are composed of a variety of complex inorganic and organic compounds, any of which might provoke allergic response in susceptible individuals. Reports of such sensitivity are atypical. However, there are individuals who may be susceptible to sensitivity, allergic or adverse reactions to composite resin restorations. The risks and benefits of all dental materials should be discussed with the patient, especially with those in susceptible populations.

Other dental materials that have elicited significant concern among dentists are nickel-chromium-beryllium alloys used predominantly for crowns and bridges. Approximately 10% of the female population are alleged to be allergic to nickel. The incidence of allergic response to dental restorations made from nickel alloys is surprisingly rare. However when a patient has a positive history of confirmed nickel allergy or when such hypersensitivity to dental restorations is suspected alternative metal alloys may be used. Discussion with the patient of the risks and benefits of these materials is indicated

Patient Name \_\_\_\_\_

I acknowledge that I have received the Dental Materials Fact Sheet, Dated October, 2001

Patient Signature \_\_\_\_\_ Date \_\_\_\_\_